

## Informal Adjunct Study Emails

Topic	Table(s)/Attachment	Email Date
Ruptures by Implant Style	Tables (not numbered): Adjunct Clinical Study Ruptures	08/06/03

### Adjunct Clinical Study Ruptures

Reconstruction		
Implant Style	Ruptures	% of Devices Enrolled (N)
Style 40	7	0.1% (5,448)
Style 45	2	0.1% (3,072)
Style 110	13	0.2% (6,448)
Style 120	2	0.1% (2,761)
Style 153	21	0.3% (8,535)
Total	45	0.2% (26,264)

Revision		
Implant Style	Ruptures	% of Devices Enrolled (N)
Style 40	7	0.1% (5,969)
Style 45	4	0.2% (2,728)
Style 110	18	0.3% (5,708)
Style 120	3	0.1% (2,203)
Style 153	7	0.3% (2,179)
Total	39	0.2% (18,787)

Total		
Implant Style	Ruptures	% of Devices Enrolled (N)
Style 40	14	0.1% (11,417)
Style 45	6	0.1% (5,800)
Style 110	31	0.3% (12,156)
Style 120	5	0.1% (4,964)
Style 153	28	0.3% (10,714)
Total	84	0.2% (45,051)

Note: There are 626 and 251 devices in the reconstruction and revision cohorts, respectively, that have not yet been classified into a device style (i.e., the implant styles are currently unknown and are being researched).